

REGRIND

Recycled Regrind rPP White Print



Name of material	Regrind rPP White Print
Country of origin	Poland
Granul size	4-14 mm
Packing	Big bags Up to 800 kg
Suggested Application	Injection, compounding

Properties	Values
Melt Flow Index [MFI] 230°C/ 2,16 kg	40-45 g/10min
Impact Charpy	7-10 kJ/m2
Density	0,91-1,0 [g/cm ³]
Chalk Content	< 4 [%]



PRODUCENT
REGRANULATÓW: PP, LDPE,LLDPE, HDPE.
PRZEMIAŁÓW: HDPE, PP

www.somex.pl

REGRIND

Recycled Regrind rPP White



Name of material	Regrind rPP White
Country of origin	Poland
Granul size	4-14 mm
Packing	Big bags Up to 800 kg
Suggested Application	Injection, compounding

Properties	Values
Melt Flow Index [MFI] 230°C/ 2,16 kg	40-45 g/10min
Impact Charpy	7-10 kJ/m2
Density	0,91-1,0 [g/cm ³]
Chalk Content	< 4 [%]



PRODUCENT
REGRANULATÓW: PP, LDPE,LLDPE, HDPE.
PRZEMIAŁÓW: HDPE, PP

www.somex.pl